



Great people. Great products.®

4000 PSI COMPRESSIVE STRENGTH CONCRETE BASED ON MINIMUM OF 28 DAYS IS UTILIZED IN ALL PRECAST POURS; STANDARD FIBERMESH @ 1.5 lbs. PCY

6 X 6 X 10 GA. / 10 GA. WELDED WIRE MATT WILL BE UTILIZED IN ALL LARGE SPAN AREAS FOR STRENGTH IN SOME APPLICATIONS, EITHER 3/8" (#3) OR 1/2" (#4) MIGHT ALSO BE UTILIZED

JOINT SEALANT IF UTILIZED IS BUTYL RUBBER MASTIC SEAL (CON SEAL) THAT CONFORMS TO AASHTO SPEC M-198 MEETS FEDERAL SPEC SS-S-0021(210-A). AND CONFORMS TO ASTM C990 SPECIFICATIONS

IF SPECIFIED, OR DAMP PROOFING IS REQUIRED, PRECAST IS COATED WITH BAY OIL, "EBONY" BRAND

SEG / PAD 13X04/5 (600#)

(5) 4" x 13.20" x 30" PADS

(120#) Each Pad

Threaded Rod's & Fastener's Provided
By Others, Not Included

