

PE 4710 SIDR – POTABLE WATER PIPE

Designed for: Water Wells – Water Service

- Standard Inside Dimension Ratio - HDPE
- BLUE - Solid Blue Pipe

Specifications:

- PE 4710 Resin formulation listed in PPI TR4
- Hydrostatic Design Basis: 1600 psi @ 73°F, 1000 psi @ 140°F
- Cell Classification per ASTM D3350 = 445574E CC3
- ASTM D2239: SIDR 7, 9
- ANSI/AWWA C901-17: SIDR 7 Only
- NSF/ANSI Standard 14 and 61

Pressure Ratings:

ASTM D2239: SIDR 9, 200 psi @ 73° F

ANSI/AWWA C901-17: SIDR 7, PC250 @ 80°F

If working temperatures exceed 80°F, contact Charter Plastics for a working pressure de-rating.

Joining:

Charter Plastics Solid Blue SIDR pipe is made to ASTM D2239 Standards for inside diameter controlled pipe. It should be joined with barbed insert fittings and clamps. Double clamping is recommended on 1-1/2" and 2" pipe in all pressures and on all PC 200 or greater pipes.

You may also use special OD Compression fittings that are designed for ASTM D2239 pipe sizes. Charter Plastics recommends roughing the end of the pipe with sandpaper prior to sliding on the fitting.

Never use any lubricant on the pipe. Do not expose the pipe to direct flame

Installing:

All Charter Plastics SIDR Potable Water Pipe can be used for down the well applications. For underground installations, the pipe can be direct buried, plowed or pulled. Buried pipe must be supported by proper embedment material like sand or gravel. Refer to PPI's "Handbook of Polyethylene Pipe" and follow as local, state or federal guidelines.

To safely handle and store polyethylene, refer to PPI's Material Handling Guide.

***This pipe is not designed for use inside the building or for hot water applications.**

Disinfection:

New water mains and service lines should be disinfected according to AWWA C651. The disinfection should take place after the initial flushing and pressure testing. Prolonged exposure or concentrated levels of disinfection chemicals may cause damage to the inside diameter of the pipe. The disinfection chemicals should never contain more than 12% active chlorine. Charter Plastics recommends the test duration not exceed 24 hours and that upon completion, the system be thoroughly flushed with fresh water.

Testing:

All pipe should be hydrostatically tested after installation.

Pneumatic testing is not recommended.

Refer to PPI's Handbook of Polyethylene Pipe for Guidelines.



Pipe for a New World.

PE 4710 SIDR – POTABLE WATER PIPE

Designed for: Water Wells – Water Service

- Standard Inside Dimension Ratio - HDPE
- BLUE - Solid Blue Pipe

PRESSURE RATING	SIZE	I.D.	MINIMUM WALL	WEIGHT PER FT
200 PSI SIDR 9	1"	1.049	.117	.195
	1.25"	1.380	.153	.329
PC 250 SIDR 7	1"	1.049	.150	.253

ANSI/AWWA C901-17
SIDR 7 Only

Weight calculations per PPI TR7

www.charterplastics.com

Charter Plastics

Polyethylene. Pipe. Partners.



Charter Plastics, Inc.

221 S. Perry Street

P.O. Box 770

Titusville PA 16354 USA

T 800 486 7473 • 814 827 9665 F
814 827 1614

Information provided in this document is accurate and reliable to the best of our knowledge. The user of such information assumes all risk connected with the use thereof. Charter Plastics Inc. assumes no responsibility for the use of information presented here in and disclaim all liability in regard to such use. For the most accurate and updated document, please refer to the latest version available online at www.charterplastics.com. Release date of this document is 6/19.